

Reference Number : PMAR/PS-1350-O/1218
 Revision Number : 1
 Effective Date : 09th Jul 2019
 Page : 1 of 3

PRODUCT SPECIFICATION

ALUMINIUM RODS GRADE EC 1350 O TEMPER [ANNEALED]

1.0 SCOPE:

This specification is main to Aluminium Wire Rods Grade EC1350 O temper: Annealed (by heat treatment on the coil) produced by Press Metal Aluminium Rods Sdn Bhd

2.0 REFERENCED SPECIFICATIONS:

ASTM B 233 Standard Specification for Aluminium 1350 Drawing stock for electrical purpose.

3.0 TECHNICAL SPECIFICATION:

3.1 DIAMETER

Specified diameter (mm)	Deviation of mean diameter from specified diameter (mm)	Deviation at any point from specified diameter (mm)
9.52	± 0.51	± 0.76

3.2 TENSILE & ELONGATION

Description (Temper)	Tensile Strength kgf/mm ²	Tensile Strength Mpa	Elongation % at 250mm GL (Min)
1350 - O	6.0 ~ 9.9	59 ~ 97	20.0

3.3 CONDUCTIVITY & RESISTIVITY

Description	Minimum Conductivity % IACS, Min	Volume electrical resistivity at 20°C ohm.mm ² /m, Max
1350 - O	61.8	0.027899

3.4 CHARACTERISTIC

Description	Unit	
Specific gravity	g/cm	2.705
Temperature coefficient at 20 °C	per °C	0.00403

Reference Number : PMAR/PS-1350-O/1218
Revision Number : 1
Effective Date : 09th Jul 2019
Page : 2 of 3

3.5 CHEMICAL COMPOSITION

Element	Composition (%)
Silicon	Max: 0.10
Iron	Max: 0.40
Copper	Max: 0.05
Manganese	Max: 0.01
Chromium	Max: 0.01
Zinc	Max: 0.05
Boron	Max: 0.05
Gallium	Max: 0.03
Vanadium & Titanium	Max: 0.02
Other elements, each	Max: 0.03
Other elements, total	Max: 0.10
Aluminium	Min: 99.5

4.0 FINISHING & APPEARANCE

The Aluminum Rod is supplied in the form of a continuous coil without any joints. The Rod shall be clean, without any excessive oil & grease, of uniform lustre, smooth and free from flakes, cracks, kinks, dents, twists, and other injury or defects.

5.0 PACKAGING

The coil shall be supplied with following dimension:

Inner diameter	Approximately 500mm
Outer diameter	1500mm maximum
Height	850mm to 950mm

The nominal weight for each coil approximately 2000 ± 200 kg.

Each coil shall be securely strapped to a timber pallet. The pallet shall be dry or free from moisture to prevent insect or fungal attack.

Adequate protection shall be provided to prevent corrosion or physical damage to the coil.

Each coil shall be wrapped with a blank polyethylene in order to be protected from damage and prevent contamination to the rods surface which might cause from the environment.

6.0 MARKING

Each coil shall be attached with waterproof label on the outside of the coil with following information:

- 1) Customer name
- 2) Material type and grade
- 3) Nominal finished rod diameter
- 4) Tested mechanical properties (Tensile and Elongation)
- 5) Conductivity
- 6) Net and gross weight
- 7) Coil identification number
- 8) Manufacturing date

Reference Number : PMAR/PS-1350-O/1218
Revision Number : 1
Effective Date : 09th Jul 2019
Page : 3 of 3

7.0 TEST CERTIFICATES

Test certificate shall be provided to customer upon or precede delivery. The contents inside the Test Certificate shall be as follows:

- 1) Customer's name
- 2) Material type and grade
- 3) Delivery Order number
- 4) Net weight
- 5) Testing result for Clause 3.0

*Requisition for additional information inside the Test Certificate shall be considered.

8.0 QUALITY ASSURANCE

All products are manufactured to meet the standard specification that been agreed between Press Metal Aluminium Rods Sdn Bhd and customer. Each of our product been tested with reliable testing equipment. Manufacturing of this product has considered the restriction of hazardous element usage stated in REACH and ROSH directive.